

PERFORMANCE DATA

TS-190 Decade 50-Year Deck Paint

COLOR(S): Wide range of colors and tint bases.

PRODUCT TYPE: Pigmented, waterborne acrylic latex polymer.

DESCRIPTION: A premium quality elastomeric acrylic solid stain suitable for most all exterior structural surfaces. Suitable for bare wooden surfaces, designed for use on properly prepared wooden surfaces including decks, railings, stairs, docks or ramps. Blocks most tannin stains with first coat. Not intended for submersion duty.

PHYSICAL CHARACTERISTICS:

DRY TO TOUCH: 1hour

DRY HARD: 24 hours

WEIGHT SOLIDS: 50%

VOLUME SOLIDS: 35%

TACK FREE: 30 minutes

TIME TO RECOAT: 24 hours, weather dependent

VISCOSITY: 90-100 K.u.

WEIGHT PER GALLON: 10.8 lbs. per gal.

V.O.C.: < 100 grams per liter

FLASH POINT: N/A.

PACKAGING: 1 or 5 gallon containers

PRACTICAL COVERAGE: 150-200 square feet per gallon @ 10 mils wet film thickness.

SURFACE PREPARATION: Clean all surfaces of corrosion, oil, grease, grime, and any existing paint lacking good adhesion. For glossy surfaces, prepare the surface by sanding lightly or applying liquid sandpaper to dull finish prior to application. **Bare Wood, Composite Siding Including Painted Surfaces:** Must be dry, thoroughly clean and free of dirt, grime, oil, grease, wax, mold, mildew and contaminates. Sanding is recommended on all surfaces for best results.

APPLICATION: May be brushed, rolled or sprayed. Apply a minimum of two coats to achieve a minimum Dry Film Thickness (DFT) of 15 mils. Roller-Coat: Recommend using a 5/8"-3/4" non-shedding roller cover. Spray: Apply a minimum of two coats to achieve minimum DFT. Brush: Apply a minimum of two coats evenly to achieve recommended DFT. Do not allow to get rain wet for 48 hours after application. Do not apply when rain is in the forecast within 48 hours. Do not apply below 50F or above 85F. Avoid applying in hot direct sunlight.

THINN & CLEAN UP: Thinning not usually required. Thin if necessary with clean water. Clean tools and equipment immediately with soap and water.