



TOP SECRET COATINGS

P.O. Box 3007, Arlington WA. 98223
 Phone: 360-651-9050 Fax: 360-548-8573
 info@topsecretcoatings.com
 www.topsecretctings.com

TS-66 Supreme Urethane (Two Component)

When You Need The Best!

Supreme Urethane (SM-266) is versatile, good looking and as durable as it gets! This two-component aliphatic acrylic urethane has been specifically formulated to provide superior adhesion, higher build and hardness along with higher chemical, heat resistance than any competing epoxy, alkyd, urethane or resin blend. It's a fully submersible self leveling formula producing superior color and gloss retention even in the heaviest duty applications. You won't find this kind of performance available anywhere else!

This unique product has its origins in government and military applications. It performs according to government specification number MIL-P-85285 so you know you are getting the best! It retains its color and gloss longer with less yellowing and chalking. Chemical resistance is remarkable!

Supreme Urethane features a high solid content formula that may be brushed, rolled or sprayed. It is dry the touch in just 30 minutes and hard enough to over coat or for light foot traffic in just six hours. It has a 4-6 hour pot life making it easy to use. Ease of application and outstanding performance makes it a compelling choice.

It has been specifically designed for extra durability and resistance to strong chemicals, high heat (500F), spilled fuel, acids, alkalis, solvents, salt spray, staining agents and corrosion over a variety of substrates. A fully submersible coating acceptable for use on virtually all interior/ exterior surfaces and infrastructure subject to corrosive marine or industrial environments. Acceptable for use above and below the waterline on concrete, prepared iron and steel, aluminum, fiberglass and wood. Available in 100 colors plus clear.

Product Features:

- Provides remarkable chemical resistance.
- Self leveling formula reduces brush and roller marks.
- Less likely to chalk, yellow or fade.
- Provides superior adhesion with higher build.
- Superior color and gloss retention.
- Withstands extremes in temperature.
- Buffing easily removes mars and abrasions.
- Long pot life makes it easy to use.
- May be brushed rolled or sprayed.
- Acceptable for long term submersion duty.
- Available in 100 colors and clear.

PERFORMANCE DATA

TS-66 Supreme Urethane (Two-Component)

COLOR(S): Available in a wide variety of colors and clear.

PRODUCT TYPE: 2-Component Acrylic Urethane.

DESCRIPTION: A premium quality, interior/exterior, two component, aliphatic acrylic urethane for use in commercial, industrial, manufacturing and marine applications. It is acceptable for constant submersion duty on a wide variety of substrates. Available in satin and gloss.

PHYSICAL CHARACTERISTICS:

VISCOSITY: +/-80 sec #4 Zahn cup. (mixed)

WEIGHT SOLIDS: 70% +/- 2 (mixed)

VOLUME SOLIDS: 53% +/-2 (mixed)

TACK FREE: 5 hours

TIME TO RECOAT: 6 hours

POT LIFE: 5 hour temp dependant

WEIGHT PER GALLON: 10.75 lbs. per gal.

DRY HARD: 8 hours

V.O.C.: 380 grams per liter (mixed)

FLASH POINT: 60 F.

PACKAGING: Quarts and 1 gallon containers (1 gallon kits).

APPLICATION: Spray. Brush and roll in small areas. This is a two-component system that is mixed just before using. MIX: 7 Volume Component A to 1 Volumes Component B. Induction time of 15 minutes should be allowed before application.

THINNING: Thin with TS-605 Thinner. Do not substitute.

CLEAN-UP: Tools and equipment may be cleaned immediately with TS-605 Thinner, acetone or lacquer thinner.